

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (original): A pressure sensitive adhesive composition
which comprises the following components (A), (B) and (C):
 - (A) An oxyalkylene polymer containing 0.3 to 0.7 equivalent of a hydrolyzable silyl group in each molecule and having a number average molecular weight of 15,000 to 100,000 (hereinafter, "hydrolyzable silyl group-containing polymer");
 - (B) A tackifier resin;
 - (C) A curing catalyst.
2. (original): The pressure sensitive adhesive composition according to Claim 1
wherein the Mw/Mn (molecular weight distribution) of the hydrolyzable silyl group-containing polymer (A) is not wider than 1.6.
3. (previously presented): The pressure sensitive adhesive composition according to Claim 1
wherein the compounding ratio of the tackifier resin (B) is 5 to 150 parts by weight per 100 parts by weight the polymer (A).

4. (previously presented): The pressure sensitive adhesive composition according to

Claim 1

wherein the hydrolyzable silyl group in the hydrolyzable silyl group-containing polymer

(A) is represented by the following general formula (I);



(wherein, R^2 represents a substituted or unsubstituted monovalent organic group containing 1 to 20 carbon atoms, X represents a hydrolyzable group, and a represents 1, 2 or 3.)

5. (previously presented): The pressure sensitive adhesive composition according to

Claim 2


wherein the compounding ratio of the tackifier resin (B) is 5 to 150 parts by weight per 100 parts by weight the polymer (A).

6. (previously presented): The pressure sensitive adhesive composition according to

Claim 2

wherein the hydrolyzable silyl group in the hydrolyzable silyl group-containing polymer

(A) is represented by the following general formula (I);



(wherein, R^2 represents a substituted or unsubstituted monovalent organic group containing 1 to 20 carbon atoms, X represents a hydrolyzable group, and a represents 1, 2 or 3.)

7. (previously presented): The pressure sensitive adhesive composition according to
Claim 3

wherein the hydrolyzable silyl group in the hydrolyzable silyl group-containing polymer
(A) is represented by the following general formula (I);



(wherein, R^2 represents a substituted or unsubstituted monovalent organic group
containing 1 to 20 carbon atoms, X represents a hydrolyzable group, and a represents 1, 2 or 3.)

8. (new): The pressure sensitive adhesive composition according to claim 1

wherein the number average molecular weight of the polymer (A) is 20,000 to 50,000.